


SOUND ABSORPTION – NRC 0.49

S50 Durra Panel Acoustic Pattern - Luxoltex Fine Finish

Product Details



S50 DURRA PANEL
ACOUSTIC PATTERN

TESTED:

Durra Panel S50mm faced with hardboard clad acoustic pattern, luxoltex finish. Overlaid with 50mm fiberglass and 125mm airspace.



REPORT:


NATA 415-82
AS 1045-1971
Louis A. Challis & Associates

REFERENCE

SA - 02

Performance Data

FREQUENCY (HZ)	100	125	160	200	250	315	400	500	630	800	1K	1.25K	1.6K	2K	2.5K	3.1K	4K	5K
ABSORPTION COEFFICIENT	.15	.15	.13	.24	.25	.44	.45	.52	.59	.62	.59	.59	.58	.59	.56	.61	.57	.68



DURRA PANEL[®]

www.durrapanel.com

Email: hello@durrapanel.com

Phone: +61 3 9580 7766

 /DURRAPANEL

 /DURRA_PANEL