


SOUND ABSORPTION – NRC 1.05

S50 Durra Panel Soundsorb - Fabric Faced 75/48

Product Details



S50 DURRA PANEL SOUNDSORB
CASSETTE: FIBREGLASS 75mm x 48kg/m³




TESTED: Durra Panel S50mm faced with 75mm x 48kg/m³ black fabric faced fibreglass.

REPORT: 1211/03-014/PD
AS 1045-1988
RMIT - NATA

REFERENCE SA - 10

Performance Data

FREQUENCY (Hz)	100	125	160	200	250	315	400	500	630	800	1K	1.25K	1.6K	2K	2.5K	3.1K	4K	5K
ABSORPTION COEFFICIENT	.45	.50	.95	.90	1.05	1.05	1.15	1.05	1.05	1.05	1.0	1.0	1.05	1.05	1.05	1.05	1.0	1.0



DURRA PANEL[®]

www.durrapanel.com
Email: hello@durrapanel.com
Phone: +61 3 9580 7766

 /DURRAPANEL
 /DURRA_PANEL